



MARPOL
EVA 2806
Ethylene Vinyl Acetate



PRODUCT DATA SHEET

PROPERTY	VALUE	ASTM
Melt Index, 190°C/ 2.16kg (g/10 min)	6.0	D 1238
Vinyl Acetate Content (%)	28	
Density (kg/m ³)	949	D 1505
Tensile Strength at Break (MPa)	16	D 638
Tensile Elongation at Break (%)	820	D 638
Flexural Modulus, 1% Secant (MPa)	19	D 790
Ring & Bell Softening Point (°C)	150	E28
Hardness, Shore A	79	D 2240
Hardness, Shore D	27	D 2240
Vicat Softening Point (°C)	44	D 1525

MARPOL® EVA 2806 contains an antioxidant to reduce viscosity changes of the hot melt blends during processing.

Recommended Applications

Hot melt coating and adhesive applications

FDA Status

Complies with Code of Federal Regulation 21 CFR Section 177.1350 and 175.105.

This information, to our knowledge, is believed to be correct. The use of this product in its actual conditions are beyond our control and satisfactory results for this product is the customer's sole responsibility.