

Daelim XP-9400



-
-
-

-
-

- 200-250

	Test Method		
	ASTM D1505	g/cm ³	0.917
(190 , 2,16)	ASTM D1238	g/10min	3.0
	ASTM D3418	°C	114
	ASTM D 882	kg/cm ²	450/370
	ASTM D 882	%	470/550
	ASTM D1004	kg/cm	120/100
	ASTM D1709	g	550
	ASTM D 1003	%	0.5

Remark> 1. 250 , 0,022
2.



TEL : 82-2-3708-3341, FAX: 82-2-753-4958

Distributed By Daelim Corporation

TEL : 82-2-3708-3312, FAX : 82-2-771-8926